

SiteSaver* Puncture Resistance Test

Performed with a 0.35" diameter steel rod.

- ◆ Puncture resistance for 80 mil HDPE is 1871 psi
- ◆ Puncture resistance for 150 mil HDPE is 3627 psi

Thickness	ASTM - D1004 Tear Resistance, lb.	ASTM - D4833 Puncture Resistance, lb.
SiteSaver™ - 150 mil	140*	349*
Poly Liner - 80 mil	75*	180*



*Patent pending. Results based on third party testing from an accredited lab. October 15, 2012

For more information call Toll Free:

855-798-7287

www.thesitesaver.com

Made in the U.S.A.



© 2014 PendaForm. 04/14
SiteSaver is a registered trademark of PendaForm.